



OC ASIAN
CONCRETO
BEAUTIFY YOUR WAY



ASIAN **HEXAGON**

HEXAGONAL PAVING STONE



ASIAN HEXAGON

Hexagonal Paving Stone

Interlocking. Super-Strong.
Low-Maintenance.

Asian Hexagon is a hexagonal paver used to create a solid, strong base through intricate interlocking of plain vertical faces. The simplicity of the Hexagon Paving Stone's shape, derived from Nature itself, creates a surface of effortless beauty, and helps render dust and slush-free aesthetically pleasant surroundings.

Special Features:

- Manufactured in 100% Automated Plant with technology from Germany
- Easy, year round installation
- Cured in heat and humidity controlled curing chamber
- Excellent skid resistance

Advantages:

- Cost-effective, less time-consuming
- High resistance to wear and mechanical damage
- Reusable and can be installed swiftly


Where to be used:

Walkways | Parking Areas | Driveways |
Rural & Community Roads | Airport Roads

Colour Range:



Laying Pattern:



Specifications:

Parameters	Dimensions
Length (mm)	226
Width (mm)	200
Thickness (mm)	50 / 60 / 70 / 80
Pavers/m ²	29.85
Pavers/ft ²	2.77
Compressive Strength (N/mm ²)	≥ 40 / ≥ 45 / ≥ 50 / ≥ 50

Load Factor:



ASIAN CONCRETO PVT. LTD.



INDIA SALES OFFICE:
Plot No. 84, Palm
Paradise, Ramgarh Taal,
Gorakhpur, UP, India
Phone: +91-8127585858

NEPAL SALES OFFICE:
1st Floor, ShriPri Home,
Kalikasthan - 29,
Kathmandu, Nepal
Phone: +977-9802711199

FACTORY:
Ramgram - 16
Nawalparasi, Nepal.
Phone: +977-9802711199

Email: info@asianconcreto.com
Website: www.asianconcreto.com
Follow us on [f](#) [@](#) [v](#) [i](#)
Asian Concreto Pvt. Ltd.

Technical Specification of Precast Concrete Pavers (Paving Block)

Product : Hexagon Paver (226x200x50)mm
 Hexagon Paver (226x200x60)mm
 Hexagon Paver (226x200x70)mm
 Hexagon Paver (226x200x80)mm

S.No.	Description	Asian Concreto				Standard References
						Nepal Standard 593:2077
1	Standard Dimension of Specimen					
	Length mm	226	226	226	226	As per Actual
	Width mm	200	200	200	200	As per Actual
	Thickness mm	50	60	70	80	As per Actual
	Aspect Ratio mm	4.52	3.77	3.22	2.82	Maximum 4
	Arris/ Chamfer mm	7.2	7.2	7.2	7.2	Min 5, Max 7
	Squareness mm	Nil	Nil	Nil	Nil	Nil
	Thickness of Wearing Layer mm	> 6	> 6	> 6	> 6	Minimum 6mm
2	Dimension Tolerance					
	Length mm	± 1mm	± 1mm	± 1mm	± 1mm	± 2mm
	Width mm	± 1mm	± 1mm	± 1mm	± 1mm	± 2mm
	Thickness mm	± 1mm	± 1mm	± 1mm	± 1mm	± 1mm
	Squareness mm	± 0mm	± 0mm	± 0mm	± 0mm	± 2mm
	Thickness of Wearing Layer mm	(+) 2mm	(+) 2mm	(+) 2mm	(+) 2mm	(+) 2mm
	Chamfer mm	(+) 0.2mm	(+) 0.2mm	(+) 0.2mm	(+) 0.2mm	± 1mm
3	Surface Area of Paver cm ²	336	336	336	336	As per Actual
4	Volume of Specimen cm ³	1680	2016	2352	2688	As per Actual
5	Minimum Compressive Strength N/mm²					(50mm) = 30N/mm ² (60mm) = 35N/mm ² (70mm) = 40N/mm ² (80mm) = 40N/mm ²
	28 Days	≥ 35	≥ 40	≥ 45	≥ 50	
6	Water Absorption (%)	< 6%	< 6%	< 6%	< 6%	Maximum 6%
7	Dry Density kg/m ³	2250	2250	2250	2250	2250 kg/m ³ , ± 50 kg/m ³
8	Abrasion Resistance mm	< 2mm	< 2mm	< 2mm	< 2mm	Maximum 3mm
9	Face Layer Pigment (Color)	Synthetic or Natural	Synthetic or Natural	Synthetic or Natural	Synthetic or Natural	Synthetic or Nautral (Zinc compound or organic dyes or Lead pigments shall not be used)
10	Lable and Marking					
	Concrete paver block package shall be marked with the following information suitably:					
	a) Identification of the manufacturer,					
	b) Grade of paver blocks, and					
c) Date of manufacture.						
Note: The product should be adequately packed to identify above and also ensure products from manufacturer facility to the buyer facility during loading transport, unloading do not suffer any physical damage including chipping, cracking, deform or any other damage from actual product specifications						